Microseal Industries Inc.

M100-APTM



Description

A clear, anti-static, heat activatable Cover Tape, for use with carrier tapes made of Polycarbonate and Polystyrene. **M100-APTM** is designed to adhere at various temperatures and dwell times within industry standards. For stronger adhesion, use a combination of higher temperature, longer dwell time and/or increased pressure.

Dimensions

M100-APTM Cover Tape is wound on a 3" plastic core in all standard widths. Splice free rolls are available in 300 meter lengths. Custom widths are available upon request.

Storage

Store at controlled room temperature 19° C to 40° C (66° F to 104° F). Relative Humidity $50 \pm 30^{\circ}$. Best if used within 24 months. Avoid excessive heat.

610 E. 36 Street Paterson, NJ 07513 Phone: 973.523.0704 Fax: 973.529.2085





Recommended Sealing Conditions

Temperature Range	130° - 210° C
Dwell Time	0.1 - 1.0 seconds
Shoe Width	0.015 - 0.020 inches
Pressure	30 psi

Properties	Value	Test method
Surface Resistivity	$<10E12 \ge 10E5$ Ohms/square (Both sides)	ASTM D-257
Tribo - Electric charge generation, adhesive tape pull test Static Decay 5kv	Less than 50 volts Less than .1 seconds	EIA - 541 Mil B-81705
Clarity Luminous Transmittance Haze Clarity	93 % 27 % 72 %	ASTM D1003
Strength Tensile Strength MD Elongation at Break MD	11,000 psi 120-140 %	ASTM D882A ASTM D882A
Peel	Completely Adjustable - Depending on Temperature	EIA 481B